

## DVM Pigments & Additives Ltd Weir Mill Crosse Hall Street

Chorley Lancashire PR6 0UH

Tel: +44 1257 278995 Fax: +44 1257 270491 Registered in England 2885951

## TECHNICAL DATA SHEET

| <b>Product Name</b> | HYDROFLEX BLUE A FDA | Version No 2  |
|---------------------|----------------------|---------------|
|                     |                      | Date Feb-2016 |

## **Product Description:**

Aqueous dispersions of CI Pigment Blue 15.0 (Phthalocyanine)

## FDA Regulations. All ingredients used comply with FDA 21CFR 177.2600 rubber articles intended for repeated use

| SPECIFICATION    |            | PROPERTIES           |                        |     |
|------------------|------------|----------------------|------------------------|-----|
| Appearance       | Blue Paste | Weather Fastness     | Full Shade             | 5   |
| Viscosity        | 30-80 dpas |                      | Reduced Shade          | 4-5 |
| Pigment %        | 44         | Heat resistance      | stance Up to 180degs C |     |
| Specific Gravity | 1.2        | Light fastness       | Full shade             | 8   |
| рН               | 7.0-9.5    |                      | Reduced shade          | 7-8 |
| Solids content   | n/a        | Resistance to alkali | 5                      |     |
| Strength         | +/- 5.0%   | Resistance to acid   | 5                      |     |
| Shade            | ΔE <2.5    | Solvent resistance   | Polar                  | 5   |
|                  |            |                      | Non-Polar              | 5   |
|                  |            |                      |                        |     |

Notes:

Light fastness Scale 1-8 1 poor 8 excellent Other fastness properties Scale 1-5 1 large change 5 small change

Packaging 30kgs